

# REHOFIX<sup>®</sup>

natural vegetable grain

## Basic raw material

natural annual plant

## Physical and chemical properties

grain size, main share	1700 µm - 2200 µm
residue on ignition (850 °C, 4 h)	approx. 1 %
pH-value	5.5 +/- 1
bulk density	500 g/l - 600 g/l
apparent density	approx. 1.0 g/ccm
flash point	approx. 185 °C
ignition point	approx. 205 °C
colour	yellow/brown

## Grain size distribution

Screen residue (with Retsch Vibrating Sieve) with an interior mesh aperture of:

<u>2500 µm</u>	<u>2000 µm</u>	<u>1600 µm</u>
max. 0.5 %	max. 30 %	50 % - 80 %

As with all natural products slight differences to the above given values may arise.

## General references

REHOFIX<sup>®</sup> vegetable grain is an environment friendly product, gained from replenishable raw materials.



J. RETTENMAIER & SÖHNE GMBH + CO  
Fibers designed by Nature  
Holzmuehle 1  
D-73494 Rosenberg

Telephone: +49 79 67/1 52 - 0  
Telefax: +49 79 67/ 1 52 - 222

0510